

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>6</sup> : C01B 31/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/02382 (43) International Publication Date: 22 January 1998 (22.01.98)</p>
<p>(21) International Application Number: PCT/US97/12042 (22) International Filing Date: 11 July 1997 (11.07.97) (30) Priority Data: 08/678,990 12 July 1996 (12.07.96) US (71) Applicant (for all designated States except US): ULTRAMET [US/US]; 12173 Montague Street, Pacoima, CA 91331 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): STANKIEWICZ, Edwin [-/US]; 11818 Riverside Drive, Valley Village, CA 91607 (US). (74) Agent: JAGGER, Bruce, A.; Brunton &amp; Jagger, P.O. Box 29000, Glendale, CA 91209-9000 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>
<p>(54) Title: A METHOD FOR PRODUCING CONTROLLED ASPECT RATIO RETICULATED CARBON FOAM AND THE RESULTANT FOAM</p> <p>(57) Abstract</p> <p>A method of manufacturing and the resultant reticulated open cell carbon foam with a controlled aspect ratio between 0.6 to 1.2 throughout the body of the foam billet by controlling the exothermic reaction of the resin system below the decomposition temperature of the foam.</p>		

BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

A METHOD FOR PRODUCING CONTROLLED ASPECT RATIO RETICULATED CARBON FOAM  
AND THE RESULTANT FOAM

Open cell vitreous carbon foam, also called  
reticulated vitreous carbon foam, is a vitreous carbon  
5 structure of three dimensional interconnected polyhedron  
cells. Vitreous carbon is a glassy carbon as opposed to a  
graphitic carbon. A cell is typically comprised of 12 to  
14 connected struts or ligaments which form a three  
dimensional polyhedron. An open cell is a cell where no  
10 film or solid is connected between the ligaments so that  
there is free communication in to and out of a cell, and  
in a group of adjoining cells all cells are  
interconnected and form a three dimensional  
interconnected structure. An open cell foam has a  
15 structure which typically consists of three dimensional  
interconnected polyhedron cells with 12 to 14 ligaments  
composing each cell, and each cell having a spheroidal  
shape.

20 The degree to which the cell shape approaches a  
perfectly spherical shape is measured by the aspect  
ratio. The aspect ratio is a dimensionless number,  
defined for the purpose of this patent application, as  
the diameter of the cell in the vertical direction  
25 divided by the diameter of the cell in the horizontal  
direction. A perfectly spherical cell would have an  
aspect ratio of 1.

The shape of the cell and hence the aspect ratio of the cell can effect the performance of the bulk vitreous carbon foam which is comprised of these cells.

5 The strength of the bulk vitreous carbon and the resistance to flow of fluids through the bulk vitreous carbon are some of the physical properties of the bulk carbon foam affected by the aspect ratio.

10 Since the physical properties of carbon foam are affected by the aspect ratio, an aspect ratio of 1 would be required for a completely isotropic foam. Users of carbon foam often desire isotropic behavior from the foam and therefore desire a foam with an aspect ratio as  
15 close to 1 as possible, and find an aspect ratio between 0.6 to 1.2 acceptable for these purposes.

Vitreous carbon foam is often coated with other materials via a chemical vapor deposition process. If the  
20 underlying vitreous carbon foam has a vast majority of cells with aspect ratios greatly different than 1 the resultant coated foam will have cells with aspect ratios greatly different than 1 and the resultant coated foam may have anisotropic properties. Chemical vapor  
25 deposition is used to coat carbon foams with ceramics such as SiC or BN and metals such as W or Ta. One application of Ta coat carbon foam is invivo exoskeleton

bone implants and tissue reception as shown by Kaplan  
U.S. Patent #5,282,861. In this particular application it  
has been found necessary to produce carbon foam billets  
at least 6" thick and as much as 8" thick where the cells  
5 of the carbon foam have an aspect ratio between 0.6 to  
1.2. Therefore there is a demonstrated commercial need  
for vitreous carbon foam of thickness greater than 6"  
having cells with aspect ratios between 0.6 to 1.2.

10

## PRIOR ART

Reticulated vitreous carbon open cell foam has  
been manufactured by first impregnating polyurethane open  
cell foam with carbonaceous thermal setting resins. The  
15 resin impregnating foam is then rapidly heated to some  
arbitrary curing temperature such as 100 C - 200 C to  
thermal set the resin. The thermal set impregnated foam  
is then heated to a suitable pyrolysis temperature, on  
the order of 800 C - 2000 C, in order to convert the  
20 carbonaceous resin in to vitreous carbon. Vinton et al,  
U.S. patent #4,022,875, discloses a method which  
endeavors to faithfully reproduce the cell geometry of  
the polyurethane foam precursor in the resultant vitreous  
carbon foam. This prior art method rapidly heats the  
25 resin impregnated foam to a curing temperature necessary  
to thermal set the resin. This prior art method makes no  
attempt to control the shape of the carbon foam cell but

targets faithful polyurethane foam geometry reproduction. Franklin U.S. patent 4,067,956 describes a method of producing an anisotropic vitreous carbon open cell foam which is compressed a minimum of 50% in only one  
5 direction. This patent physically compresses the foam a minimum of 50% in one direction during processing or uses a minimum of 50% compressed polyurethane foam precursor. The reason a minimum of 50% compression is required is that in the prior art methods a substantially uniform  
10 modification of the aspect ratio throughout the majority of the volume of the bulk foam could not be achieved unless a minimum of 50% compression or an aspect ratio of 0.5 or less was achieved.

15 Neither of aforementioned prior art patents discusses the temperature at which the carbonaceous resin undergoes an exothermic reaction and begins to crosslink and thermal set. Nor does this prior art discuss, control or employ this exotherm to specifically control or modify  
20 the cell shape within the resultant vitreous carbon foam. In the prior art attempts to faithfully reproduce the geometry of the polyurethane open cell foam precursor, this precursor typically has an aspect ratio of 1.4. In other prior art, the foam is physically compressed by at  
25 least 50 % in one direction, resulting in an aspect ratio less then or equal to 0.5.

## SUMMARY OF INVENTION

It is the object of the present invention to control the aspect ratio of the cells within the vitreous carbon foam to between 0.6 and 1.2. In the method of the present invention a polyurethane open cell foam is first impregnated with a carbonaceous resin. The open cell polyurethane foam typically has a aspect ratio of 1.3 to 1.4. This aspect ratio is not faithfully reproduced but modified during the process of the present invention to reach the desired aspect ratio of 0.6 to 1.2. The resin is comprised of a carbonaceous liquid such as furfuryl alcohol, furan or phenolic compounds, and an activating catalyst such as methyl para-toluene sulfonate, para-toluene sulfonic acid, citric acid and oxalic acid. A preferred resin for the present invention is furfuryl alcohol carbonaceous liquid and methyl para-toluene sulfonate catalyst.

The above described resin system must thermal set in an exothermic reaction which takes place below the decomposition temperature of the polyurethane foam. In the present invention exotherm temperatures of the polyurethane foam impregnated with the carbonaceous resin system are measured and a curing curve specific to each polyurethane foam impregnated with carbonaceous resin system is devised. The curing is performed in an inert

atmosphere such as nitrogen or argon, or in a non-oxidizing atmosphere such as hydrogen, or in a vacuum. After curing, the piece is carbonized to vitreous carbon in an atmosphere, as described for curing, at a  
5 suitable temperature between 900° C to 3000° C. The curing and carbonization can be performed in the same process sequence.

The curing curve will be at a heat up rate  
10 which will control the amount of exothermic heat released into the work piece at any given time and the curing curve will have specific holding temperatures at or before the exotherm temperature or temperatures in order to control the amount of heat released into a given work  
15 piece. The exotherm heat release holding temperatures are typically between 50° C to 120° C. Uncontrolled exotherms can cause a melt down of an impregnated foam or cells with undesirable aspect ratios. Insufficient exotherms or endothermic reactions would not allow the polyurethane  
20 precursor cell to be modified. The curing curve heat up rate may be controlled to 150° C to 200° C in order to fully crosslink the thermal setting resin.

The shape of the cells in the foam is modified  
25 because the heat from the exothermic reaction softens the ligaments which comprise the foam cells and the weight of the impregnated foam compresses the cell from the



polyurethane precursor aspect ratio of 1.3 to 1.4 to the desired aspect ratio of 0.6 to 1.2. The modified shape is permanently set when the resin system fully crosslinks or thermal sets. When the resin system cross links it  
5 stiffens the cell ligaments. If the resin crosslinks too quickly the polyurethane cell can not be modified sufficiently or uniformly through the body of the work piece. In some cases a weight will be placed on top of the foam to facilitate cell modification. The weight will  
10 not compress the impregnated foam by more than 20% of its thickness.

A clearer understanding of the invention will be had by reference to the following description, drawings and  
15 examples.

## BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 illustrates, in general, the steps  
5 and generalized apparatus for performing the method of  
the present invention and which method maybe used for any  
of the following examples;

Figure 2 is a graph illustrating the aspect  
ratio for one prior art foam material;

10 Figure 3 is a graph illustrating the aspect  
ratio for Example 1 of the present invention;

Figure 4 is a graph illustrating the aspect  
ratio for Example 2 of the present invention;

15 Figure 5 is a graph illustrating the aspect  
ratio for Example 3 of the present invention;

Figure 6 illustrates an example of the  
resultant foam material produced by the method of the  
present invention.

## 20 DETAILED DESCRIPTION OF THE INVENTION

The present invention will be described in  
detail with reference to three specific examples, all of  
which can be performed using the steps of the general  
25 method of Figure 1. Each example will have both specific  
times, temperatures, weights, etc. plus ranges for these

times, temperatures, weights, etc. in order to practice the present invention.

#### Example 1

5           A carbonaceous resin 10 was mixed in Step 1 in a vessel 12 using furfuryl alcohol containing 1 part per hundred methyl para-toluene sulfonate (range 0.4% to 0.4% to 8% by weight methyl para-toluene sulfonate). A piece of polyurethane foam with cells having a diameter on the order of 0.023" with aspect ratios of 1.3 to 1.4 was  
10           impregnated in step 2 with the carbonaceous resin. Excess resin was removed from the impregnated foam work piece by pressing the piece on to a perforated wooden board. The infusion of the catalyzed furfuryl resin caused the  
15           polyurethane foam to swell.

          The wet, uncured piece was then placed in a retort 16. In Step 3 the retort was filled with nitrogen and was heated with heater 18 at 0.16 degrees C per  
20           minute (range 0.05 ° C/min - 0.7 ° C/min) until it reach the exothermic heat release temperature of 70° C (range 50° C - 90° C). The piece was held at 70 C for 3 hrs. (range 1 to 15 hrs..) to allow the cell aspect ratio modification to take place. The piece was then heated at  
25           0.09 degrees C per minute (range 0. 03 ° C/ min. - 0.13° C/min) until 170° C (range 150° C - 190° C) . This second controlled ramp was necessary to allow for the complete

thermal setting of the carbonaceous resin while allowing the exothermic heat of the thermal setting to dissipate without effecting the cell shape of the work piece. The furnace was allowed to cool to room temperature and the  
5 piece was removed.

In Step 4 the piece was then relocated to a high temperature furnace 20 and heated with heater 22 to 600° C (range 400° - 800°C) over a period of 30.3 hours  
10 (range 3 - 60 hrs..). The furnace was allowed to cool to room temperature and the piece was removed. In Step 5 the piece was then relocated in to a high temperature retort furnace 24 and fired with heater 26 from room temperature to 1100°C (range 900° C - 2200°C) over a period of 7  
15 hours (range 5-56 hrs..) in order to carbonize the resin to a vitreous carbon. The furnace was allowed to cool and the product was removed. If desired, Steps 3, 4 and 5 may be performed sequentially within the same suitable furnace.

20

The resultant product of Example 1 was an open cell vitreous carbon piece with the vast majority of cells having an aspect ratio between 0.6 and 1.2 as shown in figure 3. The visual appearance of this product would  
25 be as shown in Figure 6.

The following two examples:

## Example 2

A carbonaceous resin was mixed in Step 1 using  
furfuryl alcohol containing 2 part per hundred methyl  
5 paratoluene sulfonate. A piece of polyurethane foam with  
cells having a diameter on the order of 0.023" with  
aspect ratios of 1.3 to 1.4 was impregnated in Step 2  
with the carbonaceous resin. Excess resin was removed  
from the impregnated foam work piece by pressing the  
10 piece on to a perforated wooden board. The infusion of  
the catalyzed furfuryl resin caused the polyurethane foam  
to swell.

The wet, uncured piece was then placed in a  
15 retort. In Step 3 retort was filled with nitrogen and was  
heated at .13 degrees C per minute until it reach the  
exothermic heat release temperature of 60 C. The piece  
was held at 60 C for 3 hrs. to allow the cell aspect  
ratio modification to take place. The piece was then  
20 heated at 0.1 degrees C per minute until 170 C. This  
second controlled ramp was necessary to allow for the  
complete thermal setting of the carbonaceous resin while  
allowing the exothermic heat of the thermal setting to  
dissipate without effecting the cell shape of the work  
25 piece.

The furnace was allowed to cool to room temperature and the piece was removed. Step 4 was skipped for this Example 2. In Step 5 the piece was then relocated in to a high temperature retort furnace and  
5 fired from room temperature to 1100 C over a period of 36.5 hours in order to carbonize the resin to a vitreous carbon. The furnace was allowed to cool and the product was removed. If desired, steps 3 and 5 may be performed sequentially within the same suitable furnace.

10 The resultant product of Example 2 was an open cell vitreous carbon piece with vast majority of cells having an aspect ratio between 0.6 and 1.2 as shown in Figure 4. The visual appearance of the product would be as shown in Fig. 6.

15

### Example 3

A carbonaceous resin was mixed in Step 1 using furfuryl alcohol containing 1 part per hundred methyl paratoluene sulfonate. A piece of polyurethane foam with  
20 cells having a diameter on the order of 0.023" with aspect ratios of 1.3 to 1.4 was impregnated in Step 2 with the carbonaceous resin. Excess resin was removed from the impregnated foam work piece by pressing the piece on to a perforated wooden board. The infusion of  
25 the catalyzed furfuryl resin caused the polyurethane foam to swell.

The wet, uncured piece was then placed in a retort. An uniform mass 28 (shown in Step 3 of Figure 1) such as a solid or perforated carbon plate was placed on top of the wet, uncured piece. The carbon plate was supported by the wet, uncured piece and compressed the piece 1% in the thickness direction. In step 3 the retort was filled with nitrogen and was heated at 0.18 degrees C per minute until it reach the exothermic heat release temperature of 70 C. The piece was held at 70 C for 3 hrs. to allow the cell aspect ratio modification to take place. The piece was then heated at 0.09 degrees C per minute until 170 C. This second controlled ramp was necessary to allow for the complete thermal setting of the carbonaceous resin while allowing the exothermic heat of the thermal setting to dissipate without effecting the cell shape of the work piece. The furnace was allowed to cool to room temperature and the piece was removed. Step 4 was skipped for this Examples. In step 5 the piece was then relocated in to a high temperature retort furnace and fired from room temperature to 1100 C over a period of 36.5 hours in order to carbonize the resin to a vitreous carbon. The furnace was allowed to cool and the product was removed.

The resultant of Example 3 product was an open cell vitreous carbon piece with the vast majority of cells having an aspect ratio between 0.8 and 1.2 as shown

in Figure 5. The visual appearance of the product would be as shown in Figure 6.

As these three examples show, the polyurethane foam precursor cell shape can be modified and controlled by controlled heat up rates and exotherm heat release temperature holds. The heat up rate and hold temperature(s) depend on the carbonaceous liquid, the catalyst employed, the amount of catalyst used, and the amount of cell modification desired. On commercial size pieces, all surfaces of the pyrolyzed product exhibit some distortion due to the pyrolysis process. After the pyrolysis process the distortion zones are trimmed away to yield a product with smooth faces. The bottom 5% to 10% of the smooth product may be modified below an aspect ratio of 0.6 and the top 5% to 10% of the product may not be modified to an aspect ratio of 1.2 or less. However this area of the product is generally trimmed away to yield a more aesthetically pleasing product as shown in Figure 6.

Although the invention has been described with references to a particular embodiment, it is to be appreciated that various adaptations and modifications may be made and the invention is only to be limited by the appended claims.



\_C\_L\_A\_I\_M\_S\_

I claim:

5

1. A method for producing reticulated carbon foam with a controlled aspect ratio between 0.6 to 1.2 including the following steps,

providing an open cell polyurethane foam,  
10 providing a carbonaceous thermal setting resin with said resin containing a controlled amount of well-mixed catalyst,

impregnating the foam with the resin,  
curing the impregnated foam under a controlled  
15 curing cycle in an inert or reducing atmosphere or a vacuum, wherein the controlled curing cycle includes a specific exotherm plateau temperature where the curing cycle is isothermally maintained for sufficient time to allow the first exothermic reaction of the thermal  
20 setting resin to release heat sufficient to soften the polyurethane foam ligaments and allow said foam ligaments to assume the required shape to produce the desired aspect ratio and to begin crosslinking and wherein the now partially crosslinked impregnated foam continues on  
25 the controlled curing cycle along a controlled heat-up ramp, until the resin is fully cross linked and

pyrolyzing the crosslinked foam in an inert or reducing atmosphere or vacuum until the crosslinked resin is transformed into vitreous carbon foam with cells having the shape and aspect ratio between 0.6 to 1.2  
5 created during the exothermic plateau provided during controlled curing cycle.

2. The method of claim 1 wherein the controlled curing cycle includes additional exotherm heat  
10 release plateau holding temperatures to allow for complete thermal setting of the resin.

3. The method of claim 1 wherein a uniformly distributed mass is provided and including the step of  
15 placing the mass on top of and supported by the impregnated foam before the controlled curing, to compress the impregnated foam between 0% to 20%.

4. A process as recited in claim 1 wherein a  
20 cover is provided and including the step of placing the cover on top of the impregnated foam and supported by the impregnated foam before the controlled curing to compress the impregnated foam between 0% to 20%.

5. A method for producing reticulated carbon foam with a controlled aspect ratio between 0.6 to 1.2 including the following steps,

providing an open cell polyurethane foam, providing  
5 a furfuryl alcohol with said furfuryl alcohol containing 0.4% to 8% by weight methyl para-toluene sulfonate to form a resin,  
impregnating the foam with the resin,

curing the impregnated foam under a controlled  
10 curing cycle in an inert or reducing atmosphere or a vacuum wherein the controlled curing cycle includes heating at a rate between .05° C/min to 0.7° C/min to an exotherm plateau temperature between 50° C to 90° C wherein the curing cycle is isothermally maintained for 1  
15 to 15 hours to allow the first exothermic reaction of the thermal setting resin to release heat sufficient to soften the polyurethane foam ligaments and allow said foam ligaments to assume the required shape to produce the desired aspect ratio and to begin crosslinking and  
20 wherein

the now partially crosslinked impregnated foam continues on the controlled curing cycle along a controlled heat-up ramp, at a rate of between .03 C/min to 0.13 C/min to a temperature between 150° C to 190° C  
25 until the resin is fully cross linked,

pyrolyzing the crosslinked foam to a temperature between 900 C to 1400 C in an inert or

reducing atmosphere or a vacuum until the crosslinked resin is transformed into vitreous carbon foam with cells having the shape and aspect ratio between 0.6 to 1.2 created during the exothermic plateau provided during the controlled curing cycle.

6. The method of claim 5 wherein after the foam is heated to the exotherm plateau temperatures the foam is heated to a temperature between 400° to 800° C for a period between 3 to 60 hours before the foam is pyrolyzed.

7. The method of claim 5 wherein a uniformly distributed mass is provided and including the step of placing the mass on top of and supported by the impregnated foam before the controlled curing to compress the impregnated foam between 0% to 20%.

8. The method of claim 5 wherein a cover is provided and including the step of placing the on top of the impregnated foam and supported by the impregnated foam before the controlled curing to compress the impregnated foam between 0% to 20%.

9. A reticulated carbon foam, including an open cell structure formed of these dimensional interconnected polyhedron cells formed by a vitreous carbon,


a substantial number of the cells each  
5 comprised of 12 to 14 interconnected ligaments to form a three dimensional polyhedron,

each cell having an aspect ratio defined by the diameter of the cell in a vertical direction divided by the diameter of the cell in the horizontal direction, and

10 a substantial number of the cells in the open cell structure having an aspect ratio between 0.6 to 1.2.


10. The reticulated carbon foam of claim 9 wherein the open cell structure is substantially  
15 isotropic in configuration.

FIG. 1




PRIOR ART  
**FIG. 2**

Aspect Ratio vs. Open Cell Carbon Foam Thickness




**FIG. 3**  
Aspect Ratio vs. Open Cell Carbon Foam Thickness  
Per Example Number 1





# FIG. 4

Aspect Ratio vs. Open Cell Carbon Foam Thickness  
Per Example Number 2



**FIG. 5**  
Aspect Ratio vs. Open Cell Carbon Foam Thickness  
Per Example Number 3





FIG. 6



# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US97/12042

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C01B 31/00

US CL : 423/445R; 264/29.1, 29.6, 29.7, 80

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 423/445R; 264/29.1, 29.6, 29.7, 80

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 3,927,186 A (VINTON et al) 16 December 1975, col. 2, lines 15-55.	9, 10
Y	KLEMPNER, D. and FRISCH, K. C. Polymeric Foams, 1991, pages 30, 31, 67.	9, 10

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	* &	document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means		
*P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

12 SEPTEMBER 1997

Date of mailing of the international search report

02 OCT 1997

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

RACHEL GORR

Telephone No. (703) 308-1235

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**